



920 Second Ave., Coraopolis, PA 15108
(800) 670-5767 * FAX # (412) 299-6499

TECHNICAL BULLETIN

CROSS-LINKED CLOSED CELL POLYETHYLENE CL-3

PRODUCT DESCRIPTION:

A co-polymer blend of cross-linked polyethylene specifically formulated for superior weathering characteristics.

Physical Properties	Typical Results
Normal Density PCF	2
Compression Strength @ 25% PSI	5
Compression Strength @ 50% PSI	14
Tensile Strength PSI	55
Elongation % To Break	113
Tear Resistance lb./in.	9
Compression Set % Original Thickness	28
Maximum Working Temperature (Degree Fahrenheit)	200
Minimum Working Temperature (Degree Fahrenheit)	-110
Water Absorption lbs./cut surface max.	0.04
K-Factor BTU/(hr.)(ft.2) (Degree Fahrenheit in.)	0.25

The test data shown are believed to be reliable. However, variances in testing and actual field conditions may alter the results. There is no expressed or implied warranty on the test data.