



BUILDING FASTENERS

920 Second Ave., Coraopolis, PA 15108
(800) 670-5767 * FAX # (412) 299-6499

TECHNICAL BULLETIN

NEOPRENE GROMMET

PHYSICAL PROPERTIES

	Original	Oven Aging at 100°C x 70 hrs.	Oil Immersion, ASTM at 100°C x 70 hrs.
Hardness, Shore A	60.00	63.00	43.00
Tensil, kg / cm ²	141.70	141.30	92.00
Elongation, %	380.00	335.00	260.00

Compression set, %, at 100°C x 22 hrs.

14.60

Chemical composition of Neoprene

Chloroprene
Filler - Carbon Black
Acid Acceptor MGO
Antioxidants
Ethylene Thiourea

A Body Diam.	Hole Size	Grip Range	B Length	C Head	D Head Diam.	Thread Size
.378	.378- .390	.310- .630	1.02	.050	.550	10-32

The test data shown are believed to be reliable. However, variances in testing and actual field conditions may alter the results. There is no expressed or implied warranty on the test data.